

Perfection

The ultimate 2-part polyurethane gloss finish:

Specially formulated to give the amateur user professional-quality results on topsides, superstructure and decks.

Perfection has an ultra-high gloss finish with exceptional colour and gloss retention.

A unique package of UV absorbers and HALS protect against UV attack and surface degradation, ensuring the longest lasting results.

Perfection offers exceptional durability, prolonged abrasion protection and resistance to fuels, oils, mild acids and detergents.



Colours and pack sizes available:

13 colours: Platinum A183, Mediterranean White A184, Off White A192, Snow White B000, Jade Mist Green B663, Royal Blue A216, Mauritius Blue F991, Flag Blue K990, Chilli Red E294, Cream S070, Jet Black Y999, Fighting Lady Yellow S056, Rochelle Red S299.

750 ml: All colours

Suitable Surfaces

Wood, GRP, Steel, Aluminium.

Key Features and Benefits:

1. Ultimate 2-part polyurethane gloss finish that is specially formulated for the amateur user:
 - Excellent flow delivers professional spray-quality finish by brush/roller application;
 - Step-by-step instructions demonstrate how to achieve the very best results:
See yachtpaint.com or Info CD for Instruction Leaflet and Demonstration Video.
2. Ultra-high gloss combined with longest lasting colour and gloss retention:
 - Unique package of UV absorbers and the chemically-cured polyurethane resin system protect against premature ageing from the sun.
3. Exceptional durability:
 - Resists abrasion and provides prolonged protection on areas of highest wear;
 - Resistant to fuel, oils, mild acids and detergents.

SYSTEMS AND COMPATIBILITY

Use over suitably prepared and undercoated surfaces or existing paint schemes.
Not suitable for permanently immersed surfaces.

Perfection Product Data:

PRODUCT CODE & COLOUR	YHA183 Platinum, YHA184 Mediterranean White, YHA192 Off White, YHB000 Snow White, YHB663 Jade Mist Green, YHA216 Royal Blue, YHF991 Mauritius Blue, YHK990 Flag Blue, YHE294 Chilli Red, YHS070 Cream, YHY999 Jet Black, YHS056 Fighting Lady Yellow, YHS299 Rochelle Red.
FINISH	Gloss
THINNER	International Thinner No. 9
NUMBER OF COATS	2-3
APPLICATION METHOD	Brush, Roller. Spray only using proper protective equipment and training.
PACK SIZES	750 ml
TYPICAL SHELF LIFE	2 years

Please refer to table below for Perfection drying and overcoating information. Always read the label.

Surface preparation and systems:

Previously painted surfaces:

In Good Condition: Wash down with Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.

In Poor Condition: Remove all previous coatings and prime the substrate.

PRIMING: All preparation for bare substrates is covered on the appropriate primer datasheet.

GRP: Wash down with Super Cleaner, rinse with fresh water and allow to dry. Sweep blast or abrade with 180-220 grade paper. No priming necessary.

STEEL: Prime with Interprotect®.

BARE WOOD: Prime with Interprotect or (UK only) UCP.

ALUMINIUM: Pre-prime using Etch Primer. Prime with Interprotect.

ALL SUBSTRATES: Use Perfection Undercoat

METHOD: Sand the undercoat smooth with 400 grade wet or dry paper. Dust off the hull thoroughly. Apply 2-3 coats of Perfection.

DRYING AND OVERCOATING INFORMATION

Drying								
	5°C		15°C		23°C		35°C	
Touch Dry (ISO)	11hrs		7hrs		4hrs		3hrs	
Pot Life	5hrs		3hrs		2hrs		1hr	
Overcoating								
Substrate Temperature								
	5°C		15°C		23°C		35°C	
Overcoated by:	Min	Max	Min	Max	Min	Max	Min	Max
Perfection	28hrs	4days	14hrs	3days	6hrs	2days	4hrs	1day

RELATED PRODUCTS:

PRODUCT CODE	DESCRIPTION
YMA620	Super Cleaner
YTA006	Thinner No. 9
YGB001	Curing Agent
YQA100	Accelerator for 2-part Polyurethanes
YZA900	Interspray 900 Glazecoat
YAA411	Interprotect
YPA600	UCP

International Coatings Ltd., 24-30 Canute Road, Southampton.
Tel: 023 8022 6722 Fax: 023 8033 5975

®, International®, Interprotect® and Akzo Nobel logo are registered trademarks of Akzo Nobel. © Akzo Nobel.

Disclaimer

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and, to the extent permitted by law, we can accept no responsibility for the performance of the product or for any loss or damage arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Aug 2006

